

## ROKU® V8 Gypsum Board

Fire behaviour A1 (non flammable) according to EN 15283-2-GF-C1

### Product Description

ROKU® V8 Gypsum Boards are made from various types of plaster and added cellulose fibres. The boards are heavy-duty, harmless regarding to building biology and have a high edge stability.



### Application Areas

- As surface insulation in fire protection doors
- Indoor area
- Suitable for wet rooms
- As insulation for tubular frame constructions

### Technical Data

Composition:	Hardened natural gypsum with cellulose
Material structure:	Firm panel material
Surface texture:	Smooth on both sides
Raw density [kg/m <sup>3</sup> ]:	Ca. 1100
Thermal conductivity [W/mK]:	0,280 <sup>1)</sup>
pH-value:	7

### Supplied Forms

Length:	2600 and 3030 mm ± 1,0 mm
Width:	1270 mm ± 1,0 mm
Thicknesses:	15, 18, 22 to 40 mm ± 0,3 mm

*Special formats, cuts or formed parts are available upon request are produced according to DIN 7715-5. Please observe our information for processing and the safety data sheet!*

### Processing and Storage

Processing:	Ensure that dust is minimized.
Storage:	Store in a dry area between - 20 °C and + 50 °C.

### Note

The information in this brochure is based on our knowledge and experience to date. This information does not release the user from carrying out independent tests and trials due to the various influences when processing and applying our product. It is not possible to derive a guarantee of certain properties or suitability of the product in a concrete application case based on our information. All the descriptions, drawings, photographs, data, conditions, weights etc. included may change without previous announcement; they do not constitute the contractually agreed property of the product. The recipient of our product is responsible to observe any trade mark rights and existing laws and regulations. Corresponds to DIN 2304.